

Test Report No.: HKSL1604042815TX Date: Apr 18, 2016 Page 1 of 4

REFLECTIVE APPAREL FACTORY, INC. 1649 SANDS PL SE STE. J MARIETTA, GA 30067

The following sample was submitted and identified by the client as:

One sample of knitted 100% polyester mesh, 128 (+/-5%)gsm cutting in hi-vis orange.

Country Of Destination : Global

Applicant's Proposed Care Instruction

MACHINE WASH COLD WATER, DELICATE CYCLE, WASH WITH LIKE COLORS, MILD DETERGENT, NO BLEACH, TUMBLE DRY LOW REMOVE IMMEDIATELY, DO NOT IRON, DO

NOT DRY CLEAN MAX 5 CYCLES

Sample Receiving Date : Apr 05, 2016

Test Performing Period Apr 06, 2016 – Apr 18, 2016

Test Performed : Selected tests as requested by applicant.

(details please refer to result page)

. . .

Test Results : Please refer to the next page.

Tested sample returned to applicant.

Signed for and on behalf of SGS Hong Kong Ltd.

Chan Hing Leung

Senior Technical Development Executive

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sos.com/en/Terms-and-Conditions-asses and, for electronic formal documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sos.com/en/Terms-and-Conditions/Terms-

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.





Test Report No.: HKSL1604042815TX Date: Apr 18, 2016 Page 2 of 4


Test Results:


American National Standard for High-Visibility Safety Apparel and Accessories (ANSI/ISEA 107-2015)

Background Material

Test/Method	Section	ANSI/ISEA 107 Requirement	Test Result	Pass/ Fail/ NA
Determination of Color ASTM E1164-12 (Single layer)	8.1.1 8.2.4 10.2	Test specimen must fulfill the colorimetric requirements of Table 3 for background material	As submitted: x = 0.588 y = 0.367	Pass
			%Y = 43	Pass
			After 40x Xenon: x = 0.556 y = 0.368	Pass
			%Y = 45	Pass
			After 5 Washes": x = 0.591 y = 0.367	Pass
			%Y = 45	Pass

^{*}Additional tests conducted upon client's request. Washing procedure (follow care label): AATCC 135-2012 Test No. (1)IIA(ii); Machine wash at 80 degree F with 1.8 kg total loading (Type 3 ballast + specimen) and 66±1g of 1993 AATCC Standard Reference detergent, normal cycle, tumble dry delicate less than 140 degree F





This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sos.com/en/Terms-and-Conditions.asps and, for electronic formal documents, subject to Terms and Conditions for Electronic Documents at http://www.sos.com/en/Terms-e-Document.asps.. Attention is drawn to the limitation of liability, lademilification is usual defined therein. Any hoteler or lith soccument is advised that information contained hereon reflects the Company's inidings at the time of its intervention only and within the limits of Client's Instructions, if any, The Company's sole responsibility is to its Client and this document does not expersely parties to a transaction from exercising all their rights and obligations under the transaction document. This document is unlessful and offenders may be prosecuted to the limits and the limits and the limits and obligations under the transaction document is unlessful and offenders may be prosecuted to the limits and personal and the company. Any unauthorized alteretion, lorgery or laisification of the content or supported that the limits and personal and the limits are the limits and the limits and the limits are the limits and limits and limits and limits are the limits are the limits are the limits and limits and limits are the limits are

Unless otherwise stated the results shown in this test report refer only to the sample(s) bisted and such sample(s) are retained for 30 days only.



Test Report

No.: HKSL1604042815TX

Date: Apr 18, 2016

Page 3 of 4

The chromaticity shall lie within one of the areas defined in ANSI/ISEA 107 Table 3 and the total luminance factor shall exceed the corresponding minimum in ANSI/ISEA 107 Table 3.

Color of background material and combined-performance material

Color	Chromaticity coordinates		Minimum total luminance factor	
COIOI	Х	у	Y(%)	
Fluorescent orange-red	0.610	0.390	40	
	0.535	0.375		
	0.570	0.340		
	0.655	0.345		

Test/Method	Section	ANSI/ISEA 107 Requirement	Test Result	Pass/ Fail/ NA
Colorfastness Crocking AATCC 8-2013	8.2.1	Dry 3.0 Wet 3.0	Dry: 4.5 Wet: 4.5	Pass
Colorfastness Perspiration AATCC 15-2013	8.2.2	Color change 4.0 Staining 3.0	Color change: 4.5 Staining Acetate: 4.0 Cotton: 4.5 Nylon: 4.0 Polyester:4.5 Acrylic: 4.5 Wool: 4.5	Pass
Bursting Strength (Knitted/Other Nonwovens) ASTM D3787-07 (2011); or ASTM D6797-07 (2011)	8.4.1	267 N (27.2 kgf) (60 lbf)	677.6	Pass

This document is issued by the Company subject to its General Conditions of Service printed overleas, available on request or accessable at <a href="http://www.sec.com/en/Terms-and-Conditions-for-Electronic Documents at http://www.sec.com/en/Terms-e-Document-asize. Attention is drawn to the limitation of liability, indemnification assues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's fixings at the time of its intervention only and which the limits of Clenn's instructions, if any. The Company's sobresponsibility is to its Client and this document does not expense perfect to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior writern approval of the Company. Any unauthorized aftersion, forgery or faisilication of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.



Test Report No.: HKSL1604042815TX Date: Apr 18, 2016 Page 4 of 4

TESTS AS CARE LAB			Tool Doould	I Decel
Test/Method	Section	ANSI/ISEA 107 Requirement	Test Result	Pass/ Fail/ NA
Colorfastness Domestic Laundry AATCC 61-2013-2A 105°F (modified)	8.2.3 Table 4	Color change 4.5 Staining 3.0	Color change: 4.5 Staining Acetate: 3.0 Cotton: 4.0 Nylon: 3.5 Polyester:4.5 Acrylic: 4.0 Wool: 4.5	Pass
Colorfastness Water AATCC 107-2013	8.2.3 Table 4	Color change 3.0 Staining 3.0	Color change: 4.5 Staining Acetate: 3.0 Cotton: 4.0 Nylon: 3.0 Polyester:4.5 Acrylic: 4.5 Wool: 4.5	Pass
Dimensional change Domestic AATCC 135-2012 (3)IIIA(iii)@105°F	8.3.1	Knit or Coated, Non-Woven L +/- 7% W +/-5%	5 th Cycle Length = -2.7 Width = -1.3	Pass

*** End of Report ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgc.com/en/Terms-and-Conditions and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgc.com/en/Terms-and-Conditions/Terms-and-Conditio

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.